

STAIN-PROOF M™, S-TECH 100M™, S-TECH 40M™

Surface Type	sq ft/gal.	sqm/L
Basalt - Porous (Chinese)	280	7
Basalt - Dense (European)	480	12
Bluestone (Australian Basalt)	400	10
Bluestone (USA Bluestone)	240	6
Brick	240	6
Poured Concrete	280	7
Precast Concrete	280	7
Concrete Paver (dry pressed)	160	4
Concrete Paver (wet cast)	280	7
Coral Stone	200	5
Granite Flamed	240	6
Granite Honed	320	8
Granite Polished	4800	12
Grout Lines	1200 linear feet	90 linear meters
Limestone Honed - Dense	280	7
Limestone Honed - Porous	200	5
Limestone Polished	400	10
Marble Honed	400	10
Marble Polished	600	15
Saltillo	200	5
Sandstone (Indian, hard)	280	7
Sandstone (soft)	160	4
Slate - Dense black	480	12
Slate	280	7
Terracotta dense	280	7
Terracotta porous	200	5
Travertine honed	280	7
Travertine polished	400	10

Total Application Rates include all coats. So, if for e.g. the total application rate is 200 sq. ft. per gallon (5 sq. m. per liter), and you are applying 4 coats to a vertical surface, you will apply each coat at approximately 800 sq. ft. per gallon (20 sq. m. per liter).

Please note: The information above is a rough guide only. All of the materials listed can vary in their porosity (absorbency). Always advise customers to test product on an inconspicuous area or a sample piece prior to full application.