

Slip Check to AS 4586:2013

Granite, Treated with Intensifia

NATA Accreditation Number 17139

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

Accredited for compliance with ISO/IEC 17025

NATA is a signatory to the APLAC mutual recognition arrangement for the mutual recognition of the equivalence of testing, calibration and inspection reports

16 January 2014

Test Report No. R6161b

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586:2013 Appendix A (Wet Pendulum Test)

The slip resistance Classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface.


Requested by: Dry-Treat Pty Ltd
Client Address: Unit 2, 65 Nicholson Street
St. Leonards NSW 2065
Product Manufacturer: Dry-Treat
Product Description: Granite, Treated with Intensifia

Test conducted according to: AS 4586:2013 Appendix A
Location: Slip Check Pty Ltd Test Facilities, Blacktown NSW 2148
Conducted by: Ryan Voorderhake

Date: 15 January 2014 Temperature: 29°C
Sample: Unfixed Cleaning: None
Rubber slider used: Slider 96 Conditioned: Grade P 400 paper dry followed
Slope of specimen: Tested on a flat level surface by wet lapping film
Direction of Test: NA

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	53	52	50	55	52

Reported SRV of Sample:	52
Class:	P4



Martin Daniel
Materials Scientist

16 January 2014

Test Report No. R6161b

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586:2013 Appendix B (Dry Floor Friction Test)

The slip resistance Classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface.

Requested by: Dry-Treat Pty Ltd
Client Address: Unit 2, 65 Nicholson Street
St. Leonards NSW 2065
Product Manufacturer: Dry-Treat
Product Description: Granite, Treated with Intensifia

Test conducted according to: AS 4586:2013 Appendix B
Location: Slip Check Pty Ltd Test Facilities, Blacktown NSW 2148
Conducted by: Ryan Voorderhake


Date: 15 January 2014 Temperature: 29°C
Sample: Unfixed Cleaning: Cloth
Rubber slider used: Slider 96 Conditioned: Grade P 400 paper dry

Individual measurements	#1	#2	#3	#4	#5	#6	#7	#8
Run 1	0.62	0.65	0.67	0.65	0.67	0.66	0.62	0.68
Run 2	0.74	0.77	0.74	0.75	0.82	0.76	0.70	0.70

Cumulative run length 800 mm each	Run 1	Run 2
Average Coefficient of Friction (COF)	0.65	0.75

Reported COF for Test Sample: 0.70 (Rounded to the nearest 0.05)

Class: D1



Martin Daniel
Materials Scientist