



Industrial Research Services

Materials Science and Engineering, 14 Julius Ave, North Ryde, NSW, Australia, 2113
Telephone: 61 2 9490 5614 Facsimile: 61 2 9490 5555 Email: Hugh.McMullen@csiro.au

Registered Testing Authority - CSIRO

3 September 2008

Our Ref. ES13/1609 03/0212

TEST REPORT SY 4529-7

Requested by: Drytreat Pty Ltd
Contact Name: Gabriel Chapman
on (date): 26 June 2008
Product
Descriptions: JUPARANA COLOMBO granite sealed with Dry Treat Stain Proof Meta Crème
KASHMIR WHITE granite sealed with Dry Treat Stain Proof Meta Crème
ICE BLUE granite sealed with Dry Treat Stain Proof Meta Crème
C & M CONCRETE PAVER sealed with Dry Treat Stain Proof Meta Crème
CARRARA MARBLE sealed with Dry Treat Stain Proof Meta Crème
PIETRA GREY LIMESTONE sealed with Dry Treat Stain Proof Meta Crème

JUPARANA COLOMBO granite unsealed
KASHMIR WHITE granite unsealed
ICE BLUE granite unsealed
C & M CONCRETE PAVER unsealed
CARRARA MARBLE unsealed
PIETRA GREY LIMESTONE unsealed

While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results or any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it.

The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages

SUMMARY OF TESTS PERFORMED:

AS 4459-14:1999 utilized

Determination of Resistance to Stains having filming action

Note: Results indicative. Only one sample of each material tested.

REPORT NO: 4529-7 Page 2 of 3
 ISSUE DATE: 3 September 2008
 Product Description: Various samples sealed with Dry Treat Stain Proof Meta Crème and various unsealed control samples

DETERMINATION OF RESISTANCE TO STAINS

Test Location: Ceramic Tile Laboratory Test Date: 18 August 2008

Testing conducted by: Hugh McMullen

METHOD: CSIRO applied Dry Treat Stain Proof Meta Creme in a 2-3mm thick layer, using a brush, to one sample of each of the six tiles to be tested. This crème was allowed to penetrate the tileS for 6 hours. The excess was wiped away with a cotton cloth. The treated samples sat in laboratory conditions (23°C and 55% R/H) for seven days. Another sample of each tile was left untreated as a control specimen.

After the treated samples had cured, olive oil was applied to the test specimens and the control specimens as per ISO 10545-14:1995 Clause 7.1. Attempts were made to remove the stains as per ISO 10545-14:1995 Clause 7.2.

RESULTS:

DETERMINATION OF RESISTANCE TO STAINS HAVING FILMING ACTION (INDICATIVE RESULTS ONLY)

Sample #	Sample description	Rating
1	JUPARANA COLOMBO granite sealed with Dry Treat Stain Proof Meta Crème	5
2	JUPARANA COLOMBO granite unsealed	1
3	KASHMIR WHITE granite sealed with Dry Treat Stain Proof Meta Crème	5
4	KASHMIR WHITE granite unsealed	2
5	ICE BLUE granite sealed with Dry Treat Stain Proof Meta Crème	5
6	ICE BLUE granite unsealed	1
7	C & M CONCRETE PAVER sealed with Dry Treat Stain Proof Meta Crème	5
8	C & M CONCRETE PAVER unsealed	1
9	CARRARA MARBLE sealed with Dry Treat Stain Proof Meta Crème	5
10	CARRARA MARBLE unsealed	1
11	PIETRA GREY LIMESTONE sealed with Dry Treat Stain Proof Meta Crème	5
12	PIETRA GREY LIMESTONE unsealed	2

Ratings: 5 Stain removed with a damp cloth
 4 Stain removed with a damp cloth and weak cleaning agent
 3 Stain removed with a rotating brush and strong cleaning agent
 2 Stain removed after 24 hours immersion in a suitable solvent
 1 Stain not removed



Industrial Research Services

Materials Science and Engineering, 14 Julius Ave, North Ryde, NSW, Australia, 2113
Telephone: 61 2 9490 5614 Facsimile: 61 2 9490 5555 Email: Hugh.McMullen@csiro.au

REPORT NO: 4529-7 Page 2 of 3
ISSUE DATE: 3 September 2008
Product Description: Various samples sealed with Dry Treat Stain Proof Meta Crème and various unsealed control samples

Date and Place 3 September 2008, North Ryde, NSW

Name, Title and Digital Signature:

Hugh McMullen.

HUGH McMULLEN
Technical Officer

Tel: 61 2 94905614
Fax: 61 2 94905777
Email: hugh.mcmullen@csiro.au

CSIRO