


WATERBORNE DENSE STONE SEALER

PREVIOUSLY KNOWN AS METACRÈME™

Waterborne Dense Stone Sealer is the next generation of sealing technology, the ultimate breathable impregnating sealer for protecting natural stone, tiles, masonry, pavers, concrete and grout.



TYPICAL APPLICATIONS

Waterborne Dense Stone Sealer is ideal for indoor / outdoor use on kitchens, bathrooms, entertainment areas, pool surrounds, patios, countertops, floors, walls, building facades, and for public / commercial areas.

BENEFITS

- Oil and water repellency for superior stain protection.
- Super penetration creates large water and oil-repelling barrier, which provides protection against stains and many serious problems, including efflorescence, picture framing, spalling and freeze-thaw damage.
- Retains the appearance and color of the surface. (Test before as cream can slightly darken some substrates)
- Easy, one coat application.
- Makes surfaces easier to clean, keeping them looking new for longer.
- Dries quickly, even after heavy rain.
- Breathable - water vapor escapes freely, helping to avoid harmful moisture buildup inside the treated material.
- Non-drip, Waterborne Cream. Great for vertical surfaces.
- LEED EQ Credit Conformance
LEED NC 2.2 EQ Credit 4.2: Low-Emitting Materials references South Coast Air Quality Management District (SCAQMD) Rule 1113, Architectural Coatings, rules in effect on January 1, 2004.
- Permanent bonding silanes with 50% active ingredient - no annual resealing required

VOC CONTENT

VOC (Calculated): < 100g/L

PACK SIZE

32 fl OZ / .95 L | 180013
1 Gallon / 3.79 L | 181013

HOW TO USE

1. **ALWAYS TEST PRODUCT ON A SMALL AREA FIRST** and allow a 24hr cure time to determine the ease of application and desired results.
2. Surfaces to be treated must be dry, clean and free of residues, and surface temperature between 40 - 95°F (5 - 35°C).
3. Generously coat the surface with Waterborne Dense Stone Sealer using a foam roller, brush, or similar. Avoid contact with surrounding areas.
4. Remove All excess cream in one hour, failing to remove in one hour will make it slippery and challenging to remove. Polish and remove excess with clean dry cloths (or squeegee). Estimated application rate is 1 quart per 30 to 100 square feet (1 liter per 3 to 10 sq.m.), depending on surface absorption. Applying too much will result in having to remove excess that doesn't absorb and the use of numerous of towels.
5. Use fresh water to clean equipment.
6. Avoid moisture contact with the surface for a minimum of 12 hours after application.
7. To clean treated surfaces, use Stain-Proofs Daily Floor Cleaner or Stain-Proofs Alkaline Cleaner.

NOTE: Sealer will NOT prevent surface etching, scuffing or wear and may lighten or darken some surfaces.

APPLICATION RATES

The total application rate is approximately one quart per 30 to 100 sq. feet (1 liter per three to 10 sq.m.) depending on absorption. Refer to the minimum Sealer Application Rates table for more information.

STORAGE

Store locked up in a well-ventilated place. Keep cool

DISPOSAL

Dispose of contents/container to authorized hazardous or special waste collection point in accordance with any local regulation.

COUNTRY OF MANUFACTURE

Made in the USA with globally sourced materials.

WARRANTY



*A 15-YEAR PERFORMANCE WARRANTY is offered when product applied by an Accredited Applicator following our written instructions and surface is maintained regularly using our written maintenance system, as outlined in our warranty document. Visit our website at www.stain-proof.com to find your nearest accredited applicator.



FOR MORE INGREDIENT INFORMATION, TECHNICAL DOCS, APPLICATION TIPS & COVERAGE GUIDE, SCAN THIS CODE OR VISIT: STAIN-PROOF.COM

150 Dascomb Rd, Andover, MA 01810 • USA • 1866 667 5119
30-32 Assembly Drive Tullamarine, Vic, 3043 • Australia • 1800 786 617



3rd PARTY LAB TESTING

- Depth of Penetration in Granite – 8mm
- Depth of Impregnation in Concrete Paver- 14-19mm
- ISO 10545-14:1995 Stain Test with Olive Oil – Class 5 (Highest of testing 1-5)

CAUTIONS

WARNING: Causes serious eye irritation. Causes skin irritation. May cause respiratory irritation. Suspected of damaging fertility or the unborn child. Harmful to aquatic life. **PRECAUTIONS:** Do not handle until all safety precautions have been read and understood. Avoid breathing mist/vapours/spray. Wear protective gloves/protective clothing/eye protection/face protection. Wash thoroughly after handling. Use only outdoors or in a well-ventilated area. **KEEP OUT OF REACH OF CHILDREN.**

FIRST AID

Immediately call a POISON CENTER/doctor if you feel unwell. **IF INHALED:** Remove person to fresh air and keep comfortable for breathing. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. **IF ON SKIN:** Take off immediately all contaminated clothing. Rinse skin with water/shower. **IF SWALLOWED:** Call a poison center/physician if you feel unwell. In case of fire: Use alcohol resistant foam or normal protein foam for extinction. **CONTENTS:** cyclomethicones (CAS #541-02-6 and CAS #556-67-2), polydimethylsiloxane (CAS # 68554-54-1), alkyl silane (CAS #2943-75-1), and ethoxylated alcohol (CAS # 68439-50-9).

COVERAGE GUIDE

Surface Type	sq ft/qt**	m ² /L**
Basalt - Dense (European)	120	12
Bluestone (Australian Basalt)	100	10
Bluestone (USA Boston Bluestone)	60	6
Brick	60	6
Poured Concrete - Smooth	75	7.5
Poured Concrete	70	7
Concrete Paver (dry pressed)	40	4
Concrete Paver (wet cast)	70	7
Coral Stone	50	5
Granite Flamed	60	6
Granite Honed	80	8
Granite Polished	120	12
Limestone Honed - Dense	70	7
Limestone Polished	100	10
Marble Honed	100	10
Marble Polished	150	15
Quartzite	100	10
Saltillo	50	5
Sandstone (Indian, hard)	70	7
Sandstone (soft)	40	4
Slate - Dense black	120	12
Slate	70	7
Terracotta dense	70	7
Terracotta porous	50	5
Terrazzo	100	10
Travertine honed	70	7
Travertine polished	100	10

** Minimum Coverage rates as each surface has different absorption rates. Check with your supplier

ADVANCED APPLICATION GUIDELINES

1. TESTING

Waterborne Dense Stone Sealer must be allowed to cure for at least 4 weeks before undertaking testing. Repellency will start the same day of application but full chemical bond under the surface will be a few weeks.

Achieving optimum stain repellence

Waterborne Dense Stone Sealer’s specially designed sealing molecules migrate through the pores and find sites to bond by a process of chemical reaction, over 4 to 5 weeks! As more Waterborne Dense Stone Sealer bonds inside the pores, the material becomes more oil and water-repellent. After 24 hours of cure time, the product will show only adequate stain repellency and zero penetration, but after 3 weeks cure time the results will be significantly better.

Achieving maximum depth of penetration

The modified silane molecules are hundreds of times smaller than the best modern competitor (fluorocarbon /siloxane) sealers, which cannot penetrate into the pores of dense materials, such as polished granites. With 4 hours of dwell time and 4+ weeks of cure time, typical penetration into Kashmir white granite is 7 to 13 millimeters.

2. APPLYING ON DENSE / POLISHED SURFACES

For extra penetration Waterborne Dense Stone Sealer may be left to penetrate for up to 4 hours on smaller polished surfaces such as countertops. Do not let sit for longer on porous material or floors as it can be difficult to remove.

3. APPLYING ON SMOOTH SURFACES

Once Waterborne Dense Stone Sealer has been left for at least one hour to penetrate a smooth (honed / polished / antiqued) surface, a squeegee can be used to speedily remove the bulk of the product residue. Then, the small amount of remaining excess product / residue can be easily polished off with dry absorbent cloths. If the Waterborne Dense Stone Sealer residue has begun to dry and cannot be polished off with a dry cloth, the cloth can be moistened with a small amount of Waterborne Dense Stone Sealer to aid removal.

4. APPLYING ON HIGHLY POROUS MATERIALS

Highly porous / absorbent surfaces, such as sandstone and soft varieties of limestone should be pre-sealed before applying Waterborne Dense Stone Sealer. Newly laid floors should also be pre-sealed prior to grouting, so that the grout is easy to remove and does not cause stains. Once the grout is dry and all grout haze has been thoroughly removed, Waterborne Dense Stone Sealer can be applied over the tiles and grout.

5. APPLYING ON ROUGH SURFACES

On rough surfaces, globules of Waterborne Dense Stone Sealer may collect in gaps and pits. Use a paint brush to remove these globules and spread them out.

